

# ALCHEMIX® EP 4387

Two Part, Pigmentable, Kneadable, Epoxy Putty 70 – 80 Shore D Hardness

ALCHEMIX EP 4387 is a readily pigmentable, two component epoxy putty formulated for applications such as: repair, maintenance, construction, model making and pattern making. ALCHEMIX EP 4387 is easily mixed and applied by hand and ALCHEMIX EP 4387 will bond to most substrates (metals, most plastics, rubber, ceramics, concrete, brick, wood etc) and cures at room temperature to give a tough and durable material. Once cured, the material can be machined, drilled, tapped, turned, filed, sawn, sandpapered or painted.

# Special Features

- Excellent adhesion to a variety of substrates
- Easily pigmented
- Fine texture, easy to mix
- Easy to apply

#### **Applications**

- Sealing of pipes and tanks
- Anchoring of screws and hooks
- Repairing and building-up of castings
- Repairing of shafts, bearings, pumps and casings
- Reconditioning of defective threads
- Making of patterns and models for trial series
- Repairing of aluminium, light metal and diecast parts
- Model and jewellery making

#### Mix Ratio

EP 4387 : H4387

**By Weight** 100 : 100 **By Volume** 100 : 100



#### **Product Data**

Property	Units	EP 4387	H4387
Material	-	Mineral filled	Mineral filled
		epoxy resin	hardener
Appearance	-	White putty	Pale putty
Density (25°C)	g/cm <sup>3</sup>	1.65 – 1.75	1.65 – 1.75
Workable Time (200g, 25°C)	Minutes	-	50 – 60
Full Cure (200g, 25°C)	Hours	-	24

# **Cured Properties**

Properties	Standard	Units	Result (Full Cure)
Hardness	BS 2782: Part 3: Method 365B	Shore D	70 – 80

#### Method of Use

ALCHEMIX EP 4387 should be mixed at a ratio of 100: 100 by weight or volume. The two components should be mixed by hand until of uniform colour. Insufficient mixing will result in reduced final properties or incomplete cure.

# **Pigmenting**

When used as delivered Alchemix EP 4387 yields a good white material, however, if other colours are desired then this can be easily achieved by blending in suitable pigments using the following process.

- Load EP 4387 into a suitably strong mixing vessel (planetary and Z-blade mixers are ideal)
- Add epoxy pigment paste and A802 and mix until a smooth consistent colour is achieved.

Pigment levels depend upon the desired colour strength but should not exceed 3%, the A802 level should be half of this amount, e.g. 1Kg EP 4387, 20g EP962 (Red Pigment) and 10g A802. This coloured material should then be used in the same manner as the pure white material.



### **Storage**

ALCHEMIX EP 4387 and HARDENER H4387 should be stored in original, unopened containers between 15 and 25°C.

If stored under the above conditions, ALCHEMIX EP 4387 / H4387 will have a shelf life of 12 months, from the date of production.

# **Packaging**

Please contact Alchemie Ltd

# **Further Information**

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

Our technical advice, whether verbal, or in writing is given in good faith, but without warranty - this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and use.

Before using any of our products, users should familiarize themselves with the relevant Technical and MSDS provided by Alchemie Ltd.



## **Alchemie Limited**

Alchemie Ltd develop, formulate and distribute Epoxy Resins, Polyurethane Resins, Silicones, Model Boards and Sheet Wax for use in the following applications:

- Electrical encapsulation
- Rapid Prototyping
- Prototypes
- Casting
- Gel Coating
- Laminating
- Model Making
- Master Models
- Flexible and rigid mould making

We offer fast service, technical support, development expertise, innovative products, diverse knowledge and experience.

We are a well-established company, with a high level of investment and experience. We implement BS EN ISO 9001.

Alchemie® and Alchemix® are registered Trademarks of Alchemie Ltd, Warwick Road, Kineton, Warwick, England, CV35 0HU, England, United Kingdom. Ph: +44 (0)1926 641600; FAX: +44 (0)1926 641698